

Remarks	Zinga	ZRC
Drying time to overcoat itself	30 minutes	12 hours
Drying time to handle	1 hour	12 hours
Drying time to coat with paint	24 hours	24 hours
Ph range	pH 3.0 – pH 12.5	pH6.5 – pH 10.5
Potable water approved	Yes	No
Certified as fire retardant	Yes	No
Certified by NATO	Yes	No
MoD (UK) approval	Yes	No
10 year product guarantee	Yes	No
Application on damp steel	Yes	No
Maximum working temperature	170°C	167°C
Intermittent working temp	250°C	370°C
Zinc/solvent ratio when sprayed	20:1	4:1
Minimum application temperature	-15°C	5°C
Minimum working temperature	-40°C	0°C
Contains toxic solvent residues	No	Yes